



PROPERTIES	SPEC (WT%)
Fe:	min 64.5% Reject 64%
Moisture:	Max 3.0%
SiO ₂ :	Max 5%
CCS:	Min 270 Kg/Pellet
Al ₂ O ₃ :	Max 1%
MnO:	Max 1%
FeO:	Max 1.5%
Abrasion Index:	Max 4%
S:	Max 0.08%
Tumble Index:	min 95%
P:	Max 0.08%
Porosity:	19% - 24%
TiO ₂ :	Max 0.9% reject: 1%
MgO:	0.4%
V ₂ O ₅ :	Max 0.5% Reject: 0.8%
Size:	93% (9mm>SIZE>16mm)

